

Refractive Index	n_d	1,77830 1,778300	Abbe Number	ν_d	23,91	Dispersion	n_F-n_C	0,032549
Refractive Index	n_e	1,785954	Abbe Number	ν_e	23,71	Dispersion	$n_F-n_{C'}$	0,033147

Refractive Indices		
$\lambda(\mu\text{m})$		
n_{2325}	2.32542	1,72077
n_{1970}	1.97009	1,72750
n_{1530}	1.52958	1,73544
n_{1129}	1.12864	1,74406
n_t	1.01398	1,74749
n_s	0.85211	1,75417
$n_{A'}$	0.76819	1,75917
n_r	0.70652	1,76400
n_C	0.65627	1,76902
$n_{C'}$	0.64385	1,77046
$n_{\text{He-Ne}}$	0.6328	1,77182
n_D	0.58929	1,77802
n_d	0.58756	1,77830
n_e	0.54607	1,78595
n_F	0.48613	1,80157
$n_{F'}$	0.47999	1,80361
$n_{\text{He-Cd}}$	0.44157	1,81909
n_g	0.435835	1,82191
n_h	0.404656	1,84053
n_i	0.365015	

Constants of Dispersion Formula	
A ₁	1,68236554E+00
A ₂	3,39649644E-01
A ₃	2,25049208E+00
B ₁	1,31431682E-02
B ₂	6,45040012E-02
B ₃	1,81386300E+02

Chemical Properties	
Water Resistance (Powder) Group RW(P)	1
Acid Resistance (Powder) Group RA(P)	1
Weathering Resistance (Surface) Group	2
Acid Resistance (Surface) Group SR	1.0
Phosphate Resistance PR	1.0

Mechanical Properties	
Young's Modulus E (10 ⁹ N/m ²)	753
Rigidity Modulus G (10 ⁹ N/m ²)	296
Poisson's Ratio σ	0,269
Knoop Hardness Hk [Class]	350 4
Abrasion Aa	448
Photoelastic Constant β (nm/cm/10 ⁹ Pa)	3,45

Partial Dispersions	
n_C-n_t	0,021538
$n_C-n_{A'}$	0,009855
n_d-n_C	0,009276
n_e-n_C	0,016930
n_g-n_d	0,043611
$n_g-n_{F'}$	0,020338
n_h-n_g	0,018622
n_i-n_g	
$n_{C'}-n_t$	0,022976
$n_e-n_{C'}$	0,015492
$n_{F'}-n_e$	0,017655
$n_i-n_{F'}$	

Relative Partial Dispersion	
$\theta_{C,t}$	0,6617
$\theta_{C,A'}$	0,3028
$\theta_{d,C}$	0,2850
$\theta_{e,C}$	0,5201
$\theta_{g,d}$	1,3399
$\theta_{g,F}$	0,6248
$\theta_{h,g}$	0,5721
$\theta_{i,g}$	
$\theta'_{C,t}$	0,6932
$\theta'_{e,C'}$	0,4674
$\theta'_{F,e}$	0,5326
$\theta'_{i,F'}$	

Deviation of Relative Dispersions	
$\Delta \theta_{C,t}$	0,0029
$\Delta \theta_{C,A'}$	-0,0020
$\Delta \theta_{g,d}$	0,0249
$\Delta \theta_{g,F}$	0,0220
$\Delta \theta_{i,g}$	

Thermal Properties	
Strain Point STP (°C)	520
Annealing Point AP (°C)	541
Transformation Temperature Tg (°C)	569
Yield Point At (°C)	598
Softening Point SP (°C)	630
Expansion Coefficients (-30~+70°C)	109
α (10 ⁻⁷ /°C) (+100~+300°C)	130
Thermal Conductivity k (W/m·K)	0,826

Coloring			
λ_{80}	420	λ_5	370
λ_{70}			

Internal Transmittance			
$\lambda_{0.80}$	395	$\lambda_{0.05}$	365

CCI		
B	G	R
0,00	2,61	2,69

Internal Transmittance	
$\lambda(\text{nm})$	τ 10mm
280	
290	
300	
310	
320	
330	
340	
350	
360	
370	0,11
380	0,45
390	0,74
400	0,87
420	0,949
440	0,971
460	0,980
480	0,986
500	0,990
550	0,996
600	0,997
650	0,997
700	0,997
800	0,998
900	0,998
1000	0,998
1200	0,999
1400	0,999
1600	0,995
1800	0,984
2000	0,970
2200	0,951
2400	0,920

Other Properties	
Bubble Quality Group B	
Density d	3,30
Remarks	

Temperature Coefficients of Refractive Index							
Range of Temperature (°C)	dn/dT relative (10 ⁻⁶ /°C)						
	t	C'	He-Ne	D	e	F'	g
-40~-20	-5,3	-4,5	-4,4	-4,1	-3,6	-2,3	-0,8
-20~0	-5,5	-4,5	-4,5	-4,1	-3,6	-2,2	-0,5
0~20	-5,6	-4,6	-4,5	-4,1	-3,5	-2,1	-0,3
20~40	-5,6	-4,6	-4,5	-4,1	-3,5	-2,0	-0,1
40~60	-5,7	-4,6	-4,5	-4,1	-3,5	-1,8	0,1
60~80	-5,7	-4,6	-4,5	-4,0	-3,4	-1,6	0,4